

Eurasian  
Research Bulletin

# M-10dm Oil Production Technology Based on Petroleum Distillates at Fergana Oil Refinery (For)

**Ergashev Mahmudjon  
Mamadjanovich**

PhD, Fergana Polytechnic Institute, Fergana, Uzbekistan  
E-mail: [m.ergashev@ferpi.uz](mailto:m.ergashev@ferpi.uz)

## ABSTRACT

The ever-increasing demand for lubricating oils can only be met by expanding their range in accordance with the requirements of the equipment used and the technological capabilities of the oil refining industry. A technology for producing M-10 DM engine oil using the K-471 n additive package has been developed, which provides high performance characteristics.

## Keywords:

Additives, phenols, oil, raw materials, additive, resin.

## Introduction

The severe operating conditions of high-power diesel engines, which are widespread in the territory of the Republic of Uzbekistan, impose increased requirements on the quality of engine oil. Oils intended for these purposes must, first of all, have high thermal and oxidative stability, an increased reserve of detergent-dispersant and anti-scale properties, as well as long-term anti-wear, anti-corrosion and anti-pressure properties [1].

One of the main conditions for the intensification of oil production is the constancy of the composition of oil raw materials with a high content of desirable components. A special feature of the Ferghana refinery is the use of a mixture of local high-sulfur raw materials from the Kokdumalak oil field, Kazakh oil (Kumkol) and gas condensate. The chemical composition of base oils depends on the nature of the raw material and the technological parameters of its processing processes, so a cycle of works was carried out at the Fergana oil refinery (FOR) to modernize the oil production without reducing the

selection of the target product. In order to select the most rational technology for cleaning oil distillates, which ensures the production of oils with the specified parameters and the maximum yield of the target product, the chemical composition of the raw material and the properties of its individual groups of hydrocarbons, which determine such important performance characteristics of the base oils as viscosity, viscosity index and pour point, are studied in detail [2-4].

## Materials and methods

It is shown that oil distillates and deasphaltes obtained at the Fergana oil refinery (FOR), along with high-index low-cyclic naphthenic and aromatic hydrocarbons with a high proportion of short side chains, also contain a significant amount of low-index polycyclic aromatic hydrocarbons, resins, as well as sulfur and nitrogen compounds. Analysis of the components of base oils obtained by selective purification with phenol at the FOR revealed a significant difference in their properties, which often do not meet the

criteria of international standards, according to which the carbon content in aromatic rings should not exceed 7%. In addition, base oils obtained from high-sulfur raw materials of unstable chemical composition often contain an understated number of high-index components and a lot of resins (up to 3.1 %) [5-7]. As a result, in order to obtain motor oil of the M-10 DM brand corresponding to GOST, it is

necessary to select different fractions of oil distillate obtained during complex processing, including vacuum distillation, selective purification with phenol, dewaxing and Hydrotreating [8-11]. The optimal ratio of the base components was found experimentally, providing the base oil viscosity at 100 °C within 7.5-8.5 cSt: the III fraction is 45% and the remainder is 55 %. Table-1.

**Table-1. Properties of primary components and 10 DM oil based on them**

Indicators	Components of the base oil		OIL 10 DM			
	III fraction	Residual	Actual			GOST
Kinematic viscosity, $\text{mm}^2/\text{c}$ , at 100 °C	6,8-7,8	19,45-20,82	12	11,8	11,8	>11,4
Viscosity index	96-102	94-95	97	96	100	96
The density at 20 °C, $\text{kg}/\text{dm}^3$	0,885-0,887	0,902-0,904	0,9	0,9	0,9	0,905
Base number, $\text{mg KOH}/\text{g}$			8,32	8,25	8,34	>8,2
Color on the colorimeter CNT, unit CNT with dilution 15: 85, at CNT	2,7-2,9	6,0-6,2	2,5	3,5	3,7	<3,5
Flash point, °C						
in an open crucible	210-230	200-260	224	232	244	>220
closed crucible						
Pour temperature, °C	-15	-15	-18	-18	-18	>-18
Mass fraction of mechanical impurities, %	0,0047	0,0048	0,01	0,02	0,02	<0,025
Sulphate ash content, %			0,68	0,71	0,83	<1,5
Mass fraction of active elements:			0,35	0,32	0,37	>0,03
calcium			0,1	0,09	0,1	>0,09
- zinc						
Corrosion on the plates of lead, $\text{g}/\text{m}^2$			Absent			At.

Stability over the induction period of sedimentation (NGO)			Withstands	>60
--	--	--	------------	-----

However, the complex of additives usually used to produce motor oil of the M-10 DM type proved to be insufficiently effective when injected into the resulting base oil. Therefore, employees of the Federal customs service, together with the scientific and production enterprise "Quality", conducted a study to select the composition of additives for oil type M-10 DM, providing a high level of motor performance properties. The compounding series of prototypes distillates with different color characterizing the degree of purification showed that the required level of quality end product is achieved only by using well-purified base oil, the optimum chemical composition and balanced composition of additives of polyfunctional action K-471 (table-1).

### Results

The alkaline number is one of the most important indicators of the neutralizing ability of oils, in addition, it directly or indirectly characterizes the level of performance and performance of motor oils. Sulfonates of alkaline earth metals are widely used as detergent- dispersing additives to motor oils in order to increase the alkaline number. In [12-14], it is shown that medium- alkaline additives based on alkylphenol formaldehyde condensation products are equally effective in improving the cleaning and antioxidant properties of the oil, as well as significantly reducing the tendency to varnish formation at high temperature. The effectiveness of these additives is significantly affected by the nature of the cation in their structure. For example, in terms of dispersing and anticorrosive efficiency, calcium sulfonate is somewhat superior to the corresponding barium and strontium sulfonates, but the most toxic barium sulfonate shows the greatest effect in increasing thermal stability [4-6]. In addition, sulfonates of alkaline earth metals, with a

General reduction in the content of additives in the composition, provide high physical, chemical and functional properties.

As a result of the conducted experiments, it was found that this base oil shows the greatest pick-up in relation to the package of K - 471n additives produced by JV Pharma. In addition to neutral, medium-alkaline and 'high-alkaline calcium sulfonates, the package also includes alkylphenol and succinimide additives, as well as high-temperature antioxidant additive K-34 and additive A-22. The optimal concentration (4-6 %) of the additive K-471h was found. Heavy operating conditions for the engines of quarry heavy-duty dump trucks, excavators, and similar equipment for which the M-10 DM oil is intended require increased depressor properties. This effect is achieved by the additional introduction of a special additive K-110 that modifies the crystal structure of solid hydrocarbons while maintaining the mobility of the oil at relatively low temperatures. Since many of the chemicals introduced into the base oil have foaming properties, the use of an anti - foam additive- polymethylsiloxane-is provided for accelerated foam destruction.[4] for the production of M-10DM oil, the Technological regulations and Technical conditions have been developed.

### Conclusion

Thus, the use of the K-471 n additive package in combination with the K-110 depressor additive made it possible to obtain a motor oil with high functional properties that fully complies with GOST 8581. Due to good quality, m10dm engine oil is widely used by enterprises of the Republic of Uzbekistan and is imported to the CIS and foreign countries.

## References

1. Sochevko T. I., Pakhomov M. D., Falkovich M. I., Yevtushenko V. M. (2000). Of base and commercial oils. *Chemistry and technology of fuels and oils*, (2), 37-39.
2. Sadykhov K. I., Agaev A. N., Velieva S. M. (2001). Medium-Alkaline sulfonate additive to motor oils. *Chemistry and technology of fuels and oils*, (1), 27-28.
3. Lashhi V. L., Leimeter T, Shor G. I., Falkovich M. I. (2001). Alkaline number as an indicator of compatibility of additives to engine oil. *Chemistry and technology of fuels and oils*, (5), 49-51.
4. Mamadjanovich, E. M. (2021). Technology preparation of oils for modern engines on the basis of raw material and high sulfur content. *Innovative Technologica: Methodical Research Journal*, 2(11), 127-132.
5. Эргашев, М. М. (2020). Утилизация строительных отходов-мировой опыт. *Теория и практика современной науки*, (10), 90-93.
6. Numanovich, A. I., Mamajonov, A. O., & Qosimov, L. M. (2021). Features of the properties of cement systems in the presence of mineral fillers and additives of acetone-formaldehyde resin. *Scientific and technical journal of NamIET*, 6(1), 99-108.
7. Эргашев, М. М., Мамажонов, А. У., Умирзаков, З. А., & Насирдинов, Х. Ш. (2019). Влияние наполнителя и добавки АЦФ-3М на реологические свойства цементного теста. *Проблемы современной науки и образования*, (12-2 (145)), 39-46.
8. Эргашев, М. М. (2020). Применение нанотехнологий в производстве цемента. *Экономика и социум*, (1), 952-955.
9. Мамажонов, А. У., Набиев, М. Н., & Косимов, Л. М. (2022). Раздельная технология приготовления бетонной смеси. *Universum: технические науки*, (2-2 (95)), 43-46.
10. Эргашев, М. М. (2020). Строительная индустрия узбекистана: перспективы развития. *Экономика и социум*, (1), 947-951.
11. Yunusov, M. P., Teshabaev, Z. A., Mirzaeva, E. I., Nasullaev, K. A., Ergashev, M. M., Ruzimuradov, O. N., & Murzin, D. Y. (2022). Effect of protective bed composition on deactivation of a hydrotreating catalyst. *Journal of Chemical Technology & Biotechnology*, 97(3), 771-778.
12. Solomatov, V. I., Mamajonov, A. U., Yunusaliev, E. M., & Qosimov, L. M. (2022). The formation of concrete macrostructure. *ISJ Theoretical & Applied Science*, 2(106), 170-178.
13. Эргашев, М. М. (2021). Применение строительной керамики в современной индустрии и жилищном строительстве. *Экономика и социум*, (6-2), 608-611.
14. Yunusov, M. P., Molodozhnyuk, T. B., Ergashev, M. M., Dzhalalova, S. B., Gashenko, G. A., & Saidulaev, B. M. (2007). Investigation of a system of protecting layer for the process of hydrorefining oily distillates of Uzbekistan's petroleum. *Russian Journal of Applied Chemistry*, 80(7), 1207-1212.